

**OD LITE**

OD Lite is an internal grade project emulsion paint based on a special copolymer binder. It possesses good flow and gives a smooth, flat and durable finish, OD Lite can be used on many types of surfaces, e.g. walls, ceilings, softboards and masonry surfaces.

**PHYSICAL DATA**

Colour	According to colour card
Gloss	Flat
Solid (By Volume)	35%
Specific gravity	1.45 – 1.55
Flash point	None (water as solvent)
Viscosity	120 – 125 K.U.

**RECOMMENDATION FOR USE**

Film thicknesses	Dry : 25 - 30microns – (1.0 – 1.2 mils) Wet : 71.5 – 85.8 microns – (2.9 – 3.42.4 mils)
Theoretical spreading rate at recommended film thickness	12 – 14.5 m <sup>2</sup>
Practical spreading rate (with a loss factor of 20%)	9.6 – 11.5 m <sup>2</sup>
Drying time (guiding data at ambient condition)	
Dry to touch	15 – 25 min
Dry to recoat, min	1 - 3 hours, depending to humidity
Dry to handle, min	3 – 6 hours, depending to humidity
Application methods	Brush, roller or spray-gun
Thinner/cleaner	Water
Surface preparation	The surfaces must be dry, clean and sound. Old porous and/ or chalking surfaces should be brush, cleaned and sealed with a coat of OD Lite Sealer prior to application of OD Lite. Any loose old film should be scrap off before hand.

The above information is given to the best of our knowledge based on laboratory tests and practical experience. However, as the paint is often used under conditions beyond our control, we cannot guarantee anything but the quality of the paint itself.

We reserve the right to change the given data without notice